


Technical Data

# Mackenzie Corporation

## METAL ACETYLACETONATES

MacKenzie Corporation 78015 Chemical Road Bush, Louisiana 70431 Tel: (504)-886-2173 Fax: (504)-886-2174  
E Mail Address: mlapari@mackenziechem.com

### MANGANIC ACETYLACETONATE



*tris* (2,4-Pentane dionato)manganese(III)

#### PHYSICAL PROPERTIES

Form and Appearance: Shiny Black  
Crystalline Powder

Molecular Weight: 352.24

Melting Point: 162 ° C

Boiling Point: Decomposes before Boiling

Solubility: g/100 g solvent  
Benzene: 13.86 @ 25 ° C  
Methanol: 34.84 @ 30 ° C  
n-Heptane: 00.90 @ 25 ° C

#### SPECIFICATIONS

Toluene Insolubles: 0.30 (wt) % Max  
Melting Point (° C): 160 Min  
Volatiles: 0.30 (wt) % Max

#### SUGGESTED USES

1. Source material for metal plating
2. Paint dryer
3. Intermediate for organic compounds
4. Combustion catalyst

#### AVAILABILITY

Manganic Acetylacetonate is available for immediate shipment in commercial quantities

#### CHEMICAL COMPOSITION

Manganese 15.60 %  
Carbon 51.20 %  
Hydrogen 5.98 %